

Manufacturer

Georgia-Pacific Gypsum
133 Peachtree Street
Atlanta, GA 30303

Georgia-Pacific Canada
2180 Meadowvale Boulevard, Suite 200
Mississauga, ON L5N 5S3

Technical Service Hotline: 1-800-225-6119

Description

ToughRock® Fireguard X™ and ToughRock® Fireguard C® Gypsum Board have noncombustible (per ASTM E136 or CAN/ULC S114), dimensionally stable gypsum cores. The core has been reinforced with the addition of glass fibers, increasing its strength and its resistance to the passage of heat. The surfacings on both faces and on the long edges are 100% recycled paper. The front face paper is white; the back face paper is gray. The ends are square cut.

Georgia-Pacific ToughRock Gypsum Board products are GREENGUARD and GREENGUARD Gold Certified for low emissions of volatile organic compounds (VOCs). They are listed in CHPS® High Performance Product Database as low emitting products.

Primary Uses

ToughRock Fireguard X and Fireguard C Gypsum Board are wall or ceiling covering materials for use in building construction. Both are designed for direct mechanical attachment to wood or metal framing for use in building assemblies with a designated fire resistance rating.

A specially formulated gypsum core which includes glass fibers enables ToughRock Fireguard X and Fireguard C Gypsum Board to help protect framing members from the spread of fire. With joints covered, ToughRock Fireguard X and Fireguard C Gypsum Board will resist the passage of smoke.

ToughRock Fireguard X and Fireguard C Gypsum Board are manufactured with a paper surfacing designed to be receptive to joint treatment, paint, wall covering, or textured coatings.

Limitations

- ToughRock Fireguard X and Fireguard C Gypsum Board are nonstructural products and should not be used as a nailing base or to support heavy wall mounted objects.
- They are intended for interior applications and must be kept dry and clean and not used where exposure to moisture is extreme or continuous.
- Do not use ToughRock Fireguard X and Fireguard C Gypsum Board where there is prolonged exposure to temperatures exceeding 125°F (52°C) and/or continuous exposure to extreme humidity, e.g., located adjacent to wood-burning stoves, heating appliances, electric lighting and hot air flues.

Applicable Standards

Manufactured to meet ASTM C1396 Section 5, CSA-A82.27-M; Federal SS-L-30D, Type III, Grade X and SS-6-30D.

Building Code Conformity

ToughRock Fireguard X and Fireguard C Gypsum Board conform to the requirements of uniform IBC/IRC building codes for its intended use.

Sizes

	Fireguard X™	Fireguard C®	Fireguard C®
Thickness, nominal	5/8" (15.9 mm)	5/8" (15.9 mm)	1/2" (12.7 mm)
Widths, nominal	48" (1220 mm)	48" (1220 mm)	48" (1220 mm)
Lengths, standard	8'-14' (2440-4270 mm)	8'-14' (2440-4270 mm)	8'-14' (2440-4270 mm)

Edges

Tapered, square, or tapered with rounded edges.

Supplemental Materials

Corner beads and trim, expansion joints, joint tape, joint compound.

Technical Data

Flame spread rating of 15 and smoke developed 0, when tested in accordance with ASTM E84. The core is noncombustible when tested in accordance with ASTM E136.

The 5/8" (15.9 mm) ToughRock Fireguard X is UL classified, Type X.

The 1/2" (12.7 mm) ToughRock Fireguard C is UL Type TG-C, and ULC classified, Type C.

The 5/8" (15.9 mm) ToughRock Fireguard C is UL Type TG-C, and ULC classified, Type C.

Fire Resistance Ratings

ToughRock Fireguard X and Fireguard C Gypsum Board meet the criteria for Type X special fire resistance, as defined in ASTM C1396. ToughRock Fireguard X and Fireguard C Gypsum Board are classified for fire-rated assemblies by Underwriters Laboratories LLC (UL).

Sound Control

ToughRock Fireguard X and Fireguard C Gypsum Board can achieve designated Sound Transmission Class (STC) values when used in properly designed constructions.

Sound rated assemblies require sealing at top, bottom, intersections and other locations where sound leaks may develop.

Application Standards

ToughRock Fireguard X and Fireguard C Gypsum Board may be applied according to the Gypsum Association Publication GA-216 or ASTM C840 for non-fire rated construction.

For fire resistance rated construction application regarding board orientation, fastener type and spacing shall be consistent with the tested construction details for Type X Gypsum Board. These details are published in the Gypsum Association "Fire Resistance Design Manual GA-600," "UL Fire Resistance Directory," and "Intertek Testing Services/Warnock Hersey Listings Directory."

Handling Precautions

Stack gypsum board flat on a level surface. As individual sheets are removed for installation, they should be raised up on edge carefully and carried in a vertical position. Appropriate handling is also outlined in Gypsum Association Publications GA-216 and GA-801.

Take care to avoid impact, undue flexing, and subsequent damage to board edges, ends, and corners. Avoid scuffing the face to be finished.

Handling and Use-Caution

This product may contain fiberglass which may cause skin irritation. Dust and fibers produced during the handling and installation of the product may cause skin, eye and respiratory tract irritation. Avoid breathing dust and minimize contact with skin and eyes. Wear long sleeve shirts, long pants and eye protection. Always maintain adequate ventilation. Use a dust mask or NIOSH/MSHA approved respirator as appropriate in dusty or poorly ventilated areas.

Material Safety Data Sheet

Material Safety Data Sheet (MSDS) is available upon request or online at www.buildgp.com/safetyinfo.

continued →

Submittal Approvals

Job Name _____

Contractor _____

Date _____

Stamps/Signatures

Board Decoration—Application Standards

ToughRock® Fireguard X™ and Fireguard C® Gypsum Board are designed to accept most types of paints, texture and wall covering materials. Georgia-Pacific Gypsum strongly recommends priming the surface with a full-bodied, quality latex primer before applying a final decorative material. Priming will equalize the suction variation between the joint compounds and the paper surface. If glossy paints are used in such areas as kitchens or bathrooms, skim coat joint compound over the entire surface to reduce highlighting or joint photographing. This method is also recommended in areas with severe natural or artificial side lighting.

Georgia-Pacific Gypsum recommends application of a sealer prior to applying wallpaper or other wall covering to the board so that the board surface will not be damaged if the covering is subsequently removed during redecorating. Joint treatment must be thoroughly dry before proceeding with primer application and final decoration. Refer to Gypsum Association Publications GA-214 and GA-216 for joint treatment and finishing recommendations.

Physical Properties

Properties	ToughRock® Fireguard X™	5/8" ToughRock® Fireguard C®	1/2" ToughRock® Fireguard C®
Thickness, nominal inches	5/8" (15.9 mm), ± 1/64" (0.4 mm)	5/8" (15.9 mm), ± 1/64" (0.4 mm)	1/2" (12.7 mm), ± 1/64" (0.4 mm)
Width, nominal	4' (1220 mm), 54" (1372 mm), 60" (1524 mm) ± 3/32" (2.4 mm)	4' (1220 mm) ± 3/32" (2.4 mm)	4' (1220 mm) ± 3/32" (2.4 mm)
Length, Standard	8' (2440 mm) to 14' (4270 mm), ± 1/4" (6.4 mm)	8' (2440 mm) to 14' (4270 mm), ± 1/4" (6.4 mm)	8' (2440 mm) to 14' (4270 mm), ± 1/4" (6.4 mm)
Weight ¹ , lbs./sq. ft., nominal (kg/m ²)	2.2 (10.7)	2.3 (11.2)	2.0 (9.0)
Edges	Tapered, square or tapered with rounded edges	Tapered, square or tapered with rounded edges	Tapered, square or tapered with rounded edges
Flexural Strength ² spacing, min. Parallel, lbf. (N) Perpendicular, lbf. (N)	≥ 46 (205) ≥ 147 (654)	≥ 46 (205) ≥ 147 (654)	≥ 36 (160) ≥ 107 (476)
R Value, ft ² •°F•hr/BTU (m ² •K/W)	0.56 est. (0.10)	0.56 est. (0.10)	0.48 est. (0.08)
Nail Pull Resistance ² , minimum, lbf. (N)	≥ 87 (387)	≥ 87 (389)	≥ 77 (343)
Hardness ² , lbf. (N) (core, edges and ends)	≥ 15 (67)	≥ 15 (67)	≥ 15 (67)
Humidified Deflection ² , max.	5/8" (16 mm)	5/8" (16 mm)	10/8" (32 mm)
Packaging	Two pieces per bundle, face-to-face and end taped	Two pieces per bundle, face-to-face and end taped	Two pieces per bundle, face-to-face and end taped
Surface Burning Characteristics ³ (per ASTM E84) Flame Spread Smoke Developed (Core is noncombustible when tested in accordance with ASTM E136.)	15 0	15 0	15 0

¹ Represents approximate weight for design and shipping purposes. Actual weight may vary depending on manufacturing location and other factors.

² Specified minimum values are as defined in ASTM C1396.

³ Products qualify for NFPA Class A or IBC Class 1.



Georgia-Pacific
Gypsum

U.S.A. Georgia-Pacific Gypsum LLC
Georgia-Pacific Gypsum II LLC
Canada Georgia-Pacific Canada LP

SALES INFORMATION AND ORDER PLACEMENT

U.S.A. West: 1-800-824-7503
Midwest: 1-800-876-4746
South Central: 1-800-231-6060
Southeast: 1-800-327-2344
Northeast: 1-800-947-4497

CANADA Canada Toll Free: 1-800-387-6823
Quebec Toll Free: 1-800-361-0486

TECHNICAL INFORMATION

U.S.A. and Canada: 1-800-225-6119, www.gpgypsum.com

TRADEMARKS TOUGHRock, FIREGUARD X, FIREGUARD C and the GEORGIA-PACIFIC logo are trademarks owned by or licensed to Georgia-Pacific Gypsum LLC. Collaborative for High Performance Schools and CHPS are trademarks owned by Collaborative for High Performance Schools, Inc.

WARRANTIES, REMEDIES AND TERMS OF SALE For current warranty information for this product, please go to www.gpgypsum.com and select the product for warranty information. All sales of this product by Georgia-Pacific are subject to our Terms of Sale available at www.gpgypsum.com.

UPDATES AND CURRENT INFORMATION The information in this document may change without notice. Visit our website at www.gpgypsum.com for updates and current information.

CAUTION For product fire, safety and use information, go to www.buildgp.com/safetyinfo or call 1-800-225-6119.

FIRE SAFETY CAUTION Passing a fire test in a controlled laboratory setting and/or certifying or labeling a product as having a one-hour, two-hour, or any other fire resistance or protection rating and, therefore, as acceptable for use in certain fire rated assemblies/systems, does not mean that either a particular assembly/system incorporating the product, or any given piece of the product itself, will necessarily provide one-hour fire resistance, two-hour fire resistance, or any other specified fire resistance or protection in an actual fire. In the event of an actual fire, you should immediately take any and all actions necessary for your safety and the safety of others without regard for any fire rating of any product or assembly/system.

SUBMITTAL IDENTIFICATION SHEET

To be completed by Contractor/CM

WEBSTER UNIVERSITY ISB

PROJECT NAME

8274 BIG BEND BLVD

ADDRESS

NUMBER

WEBSTER UNIVERSITY

OWNER

CANNON DESIGN

ARCHITECT / ENGINEER

Joe Voypick

SUBMITTED BY

092900-006

CONTRACTOR / CM SUBMITTAL NO.

CANNON DESIGN SUBMITTAL NO.

Marino Ware

DRAWING / DETAIL REFERENCE

092900

SPECIFICATION SECTION / PARAGRAPH

MANUFACTURER / SUPPLIER

ITEM / PRODUCT ID

REQUIRED DATE

PRIORITY

CRITICAL

ITEM BEING SUBMITTED (check only one)

- ☐ Shop Drawings
☐ Samples
☐ (____ copies)
☐ LEED Submittal
☐ Other _____
- ☐ Certification / Qualifications
☐ Record Documents
☒ Product Data
- ☐ Coordination Drawing
☐ Calculations
☐ Schedules
☐ O&M Manuals

ITEM BEING SUBMITTED FOR (check only one)

- ☒ Action
☐ Information Only
☐ Record

REMARKS OR DEVIATIONS

Includes:
-Regular and Fire Code Cores
-Mold Tough Panels

CONTRACTOR / CM CERTIFICATION
(SUBMITTALS NOT CERTIFIED WILL BE RETURNED WITHOUT REVIEW)



PARIC CORPORATION
SUBMITTAL STAMP

THIS SHOP DRAWING HAS BEEN REVIEWED BY PARIC CORPORATION

Subcontractor remains responsible for dimensions, quantities, coordination with other trades and compliance with contract documents.

By:

Devin D. Gates

To be completed by Reviewer

09 2900-006

CANNON DESIGN SUBMITTAL NUMBER

9/8/16

RECEIVED DATE

- ☐ A. No Exceptions Taken
No further review of submittal is required.
- ☒ B. Make Corrections Noted
Incorporate corrections in work; resubmission is not required.
- ☐ C. Revise and Resubmit
Revise as noted, and resubmit for review.
- ☐ D. Rejected
Submittal is not in compliance with Contract Documents; provide new submittal.
- ☐ E. For Record / Information Only
Submittal was reviewed for Record / Information purposes only.
- ☐ F. Not Required for Review
Submittal is not required by Contract Documents and has not been reviewed.

Review is for conformance with the design concept of this project and for general compliance with contract documents. Contractor is responsible for quantities, dimensions and compliance with contract documents and for information that pertains to fabrication processes, construction techniques and coordination of this work with all trades which will be affected thereby. This review is null and void if submittal deviates from contract documents and does not indicate or note deviations.

A/E COMMENTS

☐ See attached sheet(s) for additional comments

Joe Voypick

REVIEWED BY

9/7/16

DATE

Kelvin Patel

REVIEWED BY

Digitally signed by Kelvin Patel
Date: 2016.09.16 15:53:04-05'00'

09/16/16

DATE



77 Westport Plaza
Suite 250
St. Louis, MO 63146

TRANSMITTAL

No. 15051-0210

Paric Corporation

PROJECT: 15051-Webster University Interdisciplinary Science Building

DATE: 09/07/2016

TO: Cannon Design
1100 Clark Ave
St Louis MO 63102

RE: Sheetrock Gypsum Panels Product Data

ATTN: Kelvin Patel

JOB: 15051

WE ARE SENDING:	SUBMITTED FOR:	ACTION TAKEN:
☐ Shop Drawings	☒ Approval	☐ Approved as Submitted
☐ Letter	☐ Your Use	☐ Approved as Noted
☐ Prints	☐ As Requested	☐ Returned After Loan
☐ Change Order	☐ Review and Comment	☐ Resubmit
☐ Plans		☐ Submit
☐ Samples	SENT VIA:	☐ Returned
☐ Specifications	☐ Attached	☐ Returned for Corrections
☒ Other: Product Data	☐ Separate Cover Via:	☐ Due Date:

Item	Package	Code	Rev.	Copies	Date	Description	Status
Submittal		092900-006	1		09/07/2016	Sheetrock Gypsum Panels Product Data	Submitted

NOTES:

CC:

Signed: _____
Devin Gates