



PRO

INDUSTRIAL™

PRO-CRYL® UNIVERSAL PRIMER

As of 09/11/2015, Complies with:			
OTC	Yes	LEED® 09 CI	Yes
SCAQMD	Yes	LEED® 09 NC	Yes
CARB	Yes	LEED® 09 CS	Yes
CARB SCM 2007	Yes	LEED® 09 S	Yes
MPI	107,134	NGBS	Yes

B66W00310
B66A00310
B66N00310

OFF WHITE
GRAY
RED OXIDE

CHARACTERISTICS

Pro Industrial Pro-Cryl Universal Primer is an advanced technology, self cross-linking acrylic primer. It is rust inhibitive and designed for commercial, new construction and maintenance applications. It can be used as a primer under water-based or solvent-based high performance topcoats.

- Rust inhibitive
- Single component
- Early moisture resistant
- Fast dry
- Low temperature application 40°F
- Interior and exterior use
- Suitable for use in USDA inspected facilities

Color: Off White, Gray, Red Oxide

Recommended Spread Rate per coat:

Wet mils: 5.0 - 10.0
Dry mils: 1.8 - 3.6
~Coverage: 160 - 320 sq ft/gal
Approximate

Theoretical coverage sq ft/gal

(m2/L) @ 1 mil / 25 microns dft 577sq ft
NOTE: Brush or roll application may require multiple coats to achieve maximum film thickness and uniformity of appearance.

Drying Time @ 6.0 mils wet 50% RH:

	40°F	77°F	120°F
To touch:	2 hrs	40 min	20 min
Tack free:	8 hrs	2 hrs	1 hr
To recoat:	16 hrs	4 hrs	2 hrs
To cure:	45 days	30 days	14 days

Drying time is temperature, humidity, and film thickness dependent.

Finish: Low sheen

Flash Point: N/A

Shelf Life: 36 months, unopened
Store indoors at 40°F to 100°F.

Tinting: Do not tint

B66W310 (may vary by color)

VOC (less exempt solvents):

96 g/L; 0.80 lb/gal

As per 40 CFR 59.406 and SOR/2009-264, s.12

Volume Solids: 36% ± 2%

Weight Solids: 49% ± 2%

Weight per Gallon: 10.23 lb

RECOMMENDED SYSTEMS

Waterborne topcoat:

1-2 cts. Pro Industrial Acrylic
or Pro Industrial DTM Acrylic
or Pro Industrial Multi-Surface Acrylic
or Pro Industrial Pre-Catalyzed Waterbased Epoxy
or Pro Industrial Waterbased Acrolon 100
or Pro Industrial Waterbased Catalyzed Epoxy

Solventborne topcoat:

1-2 cts. Pro Industrial High Performance Epoxy
or Pro Industrial Urethane Alkyd

Pro Industrial Pro-Cryl Universal Primer B66W310 Off White is GREENGUARD GOLD certified for low chemical emissions into indoor air during product usage. For more information, visit ul.com/gg.

System Tested: (unless otherwise indicated)

Substrate: Steel
Surface Preparation: SSPC-SP10
1 ct. Pro Industrial Pro-Cryl Universal Primer
1 ct. Pro Industrial Acrylic

Adhesion:

Method: ASTM D4541
Result: 500 psi

Corrosion Weathering:

Method: ASTM D5894, 10 cycles,
3360 hours
Result: Passes

Direct Impact Resistance:

Method: ASTM D2794
Result: >140 in. lbs.

Dry Heat Resistance*:

Method: ASTM D2485
Result: 200°F

Flexibility:

Method: ASTM D522, 180° bend,
1/4" mandrel
Result: Passes

Moisture Condensation Resistance:

Method: ASTM D4585, 100°F, 1250
hours
Result: Passes

Pencil Hardness:

Method: ASTM D3363
Result: H

Salt Fog Resistance:

Method: ASTM B117, 1250 hours
Result: Passes

Provides performance comparable to products formulated in lieu of Federal Specification: AA50557 and Paint Specification: SSPC-Paint 23.

*Suitable for intermittent dry heat resistance up to 300°F when used as a system with Sher-Cryl HPA

PRO INDUSTRIAL™
PRO-CRYL® UNIVERSAL PRIMER



SHERWIN-WILLIAMS.

SURFACE PREPARATION

WARNING! Removal of old paint by sanding, scraping or other means may generate dust or fumes that contain lead. Exposure to lead dust or fumes may cause brain damage or other adverse health effects, especially in children or pregnant women. Controlling exposure to lead or other hazardous substances requires the use of proper protective equipment, such as a properly fitted respirator (**NIOSH** approved) and proper containment and cleanup. For more information, call the National Lead Information Center at **1-800-424-LEAD** (in US) or contact your local health authority.

Do not use hydrocarbon solvents for cleaning.

Iron & Steel - Minimum surface preparation is Hand Tool Cleaning per SSPC-SP2. Remove all oil and grease from the surface per SSPC-SP1. For better performance, use Commercial Blast Cleaning per SSPC-SP6.

Aluminum - Remove all oil, grease, dirt, oxide and other foreign material per SSPC-SP1. Prime the area the same day as cleaned.

Galvanizing - Allow to weather a minimum of six months prior to coating. Solvent Clean per SSPC-SP1. When weathering is not possible, or the surface has been treated with chromates or silicates, first Solvent Clean per SSPC-SP1 and apply a test patch. Allow paint to dry at least one week before testing adhesion. If adhesion is poor, brush blasting per SSPC-SP16 is necessary to remove these treatments. Rusty galvanizing requires a minimum of Hand Tool Cleaning per SSPC-SP2, prime the area the same day as cleaned.

Previously Painted Surfaces - If in sound condition, clean the surface of all foreign material. Smooth, hard or glossy coatings and surfaces should be dulled by abrading the surface. Apply a test area, allowing paint to dry one week before testing adhesion. If adhesion is poor, additional abrasion of the surface and/or removal of the previous coating may be necessary. Retest surface for adhesion. If paint is peeling or badly weathered, clean surface to sound substrate and treat as a new surface as above. Recognize that any surface preparation short of total removal of the old coating may compromise the service length of the system.

APPLICATION PROCEDURES

Apply paint at the recommended film thickness and spreading rate as indicated on front page. Application of coating below minimum recommended spreading rate will adversely affect coating performance.

SAFETY PRECAUTIONS

Refer to the SDS sheets before use. **FOR PROFESSIONAL USE ONLY**

Published technical data and instructions are subject to change without notice. Contact your Sherwin-Williams representative for additional technical data and instructions.

PERFORMANCE TIPS

No painting should be done immediately after a rain or during foggy weather.

When using spray application, use a 50% overlap with each pass of the gun to avoid holidays, bare areas, and pinholes. Apply coating evenly while maintaining a wet edge to prevent lapping.

APPLICATION

Refer to the SDS before using

Temperature: 40°F minimum
120°F maximum
(air, surface, and material)
At least 5°F above dew point

Relative humidity: 85% maximum

The following is a guide. Changes in pressures and tip sizes may be needed for proper spray characteristics. Always purge spray equipment before use with listed reducer. Any reduction must be compatible with the existing environmental and application conditions.

Reducer: Water

Airless Spray

Pressure2000 psi
Hose 1/4" ID
Tip015" - .019"
Filter 60 mesh
ReductionNot recommended

Conventional Spray

Gun Binks 95
Fluid Nozzle 66
Air Nozzle 63PB
Atomization Pressure60 psi
Fluid Pressure25 psi
ReductionAs needed up to 5% by volume

Brush Nylon/Polyester
ReductionNot recommended

Roller3/8" woven
ReductionAs needed up to 5% by volume

If specific application equipment is listed above, equivalent equipment may be substituted.

CLEANUP INFORMATION

Clean spills and spatters immediately with soap and warm water. Clean hands and tools immediately after use with soap and warm water. After cleaning, flush spray equipment with compliant cleanup solvent to prevent rusting of the equipment. Follow manufacturer's safety recommendations when using solvents.

HOTW 09/11/2015 B66W00310 32 96

KOR, FRC, SP

Material Safety Data Sheets

MATERIAL SAFETY DATA SHEET

B66W310
34 00

DATE OF PREPARATION
Dec 23, 2016

SECTION 1 — PRODUCT AND COMPANY IDENTIFICATION

PRODUCT NUMBER

B66W310

PRODUCT NAME

PRO INDUSTRIAL™ PRO-CRYL® Universal Acrylic Primer, Off White

MANUFACTURER'S NAME

THE SHERWIN-WILLIAMS COMPANY
101 W. Prospect Avenue
Cleveland, OH 44115

Telephone Numbers and Websites

Product Information	(800) 524-5979 www.sherwin-williams.com
Regulatory Information	(216) 566-2902 www.paintdocs.com
Medical Emergency	(216) 566-2917
Transportation Emergency*	(800) 424-9300
*for Chemical Emergency ONLY (spill, leak, fire, exposure, or accident)	

SECTION 2 — COMPOSITION/INFORMATION ON INGREDIENTS

% by Weight	CAS Number	Ingredient	Units	Vapor Pressure
3	29911-28-2	1-(2-Butoxymethylethoxy)-propanol		
		ACGIH TLV	Not Available	0.06 mm
		OSHA PEL	Not Available	
13	1317-65-3	Calcium Carbonate		
		ACGIH TLV	10 mg/m3 as Dust	
		OSHA PEL	10 mg/m3 Total Dust	
		OSHA PEL	5 mg/m3 Respirable Fraction	
9	13463-67-7	Titanium Dioxide		
		ACGIH TLV	10 mg/m3 as Dust	
		OSHA PEL	10 mg/m3 Total Dust	
		OSHA PEL	5 mg/m3 Respirable Fraction	

SECTION 3 — HAZARDS IDENTIFICATION

ROUTES OF EXPOSURE

INHALATION of vapor or spray mist.

EYE or SKIN contact with the product, vapor or spray mist.

EFFECTS OF OVEREXPOSURE

EYES: Irritation.

SKIN: Prolonged or repeated exposure may cause irritation.

INHALATION: Irritation of the upper respiratory system.

In a confined area vapors in high concentration may cause headache, nausea or dizziness.

SIGNS AND SYMPTOMS OF OVEREXPOSURE

Redness and itching or burning sensation may indicate eye or excessive skin exposure.

MEDICAL CONDITIONS AGGRAVATED BY EXPOSURE

None generally recognized.

CANCER INFORMATION

For complete discussion of toxicology data refer to Section 11.

HMIS Codes

Health	1*
Flammability	0
Reactivity	0

SECTION 4 — FIRST AID MEASURES

EYES: Flush eyes with large amounts of water for 15 minutes. Get medical attention.

SKIN: Wash affected area thoroughly with soap and water.
Remove contaminated clothing and laundry before re-use.

INHALATION: If affected, remove from exposure. Restore breathing. Keep warm and quiet.

INGESTION: Do not induce vomiting. Get medical attention immediately.

SECTION 5 — FIRE FIGHTING MEASURES

FLASH POINT

Not Applicable

LEL

Not
Applicable

UEL

Not
Applicable

FLAMMABILITY CLASSIFICATION

Not Applicable

EXTINGUISHING MEDIA

Carbon Dioxide, Dry Chemical, Alcohol Foam

UNUSUAL FIRE AND EXPLOSION HAZARDS

Closed containers may explode (due to the build-up of pressure) when exposed to extreme heat.

During emergency conditions overexposure to decomposition products may cause a health hazard. Symptoms may not be immediately apparent. Obtain medical attention.

SPECIAL FIRE FIGHTING PROCEDURES

Full protective equipment including self-contained breathing apparatus should be used.

Water spray may be ineffective. If water is used, fog nozzles are preferable. Water may be used to cool closed containers to prevent pressure build-up and possible autoignition or explosion when exposed to extreme heat.

SECTION 6 — ACCIDENTAL RELEASE MEASURES

STEPS TO BE TAKEN IN CASE MATERIAL IS RELEASED OR SPILLED

Remove all sources of ignition. Ventilate the area.

Remove with inert absorbent.

SECTION 7 — HANDLING AND STORAGE

STORAGE CATEGORY

Not Applicable

PRECAUTIONS TO BE TAKEN IN HANDLING AND STORAGE

Keep container closed when not in use. Transfer only to approved containers with complete and appropriate labeling. Do not take internally.

Keep out of the reach of children.

SECTION 8 — EXPOSURE CONTROLS/PERSONAL PROTECTION

PRECAUTIONS TO BE TAKEN IN USE

Use only with adequate ventilation.

Avoid contact with skin and eyes. Avoid breathing vapor and spray mist.

Wash hands after using.

This coating may contain materials classified as nuisance particulates (listed "as Dust" in Section 2) which may be present at hazardous levels only during sanding or abrading of the dried film. If no specific dusts are listed in Section 2, the applicable limits for nuisance dusts are ACGIH TLV 10 mg/m³ (total dust), 3 mg/m³ (respirable fraction), OSHA PEL 15 mg/m³ (total dust), 5 mg/m³ (respirable fraction).

VENTILATION

Local exhaust preferable. General exhaust acceptable if the exposure to materials in Section 2 is maintained below applicable exposure limits. Refer to OSHA Standards 1910.94, 1910.107, 1910.108.

RESPIRATORY PROTECTION

If personal exposure cannot be controlled below applicable limits by ventilation, wear a properly fitted organic vapor/particulate respirator approved by NIOSH/MSHA for protection against materials in Section 2.

When sanding or abrading the dried film, wear a dust/mist respirator approved by NIOSH/MSHA for dust which may be generated from this product, underlying paint, or the abrasive.

PROTECTIVE GLOVES

Wear gloves which are recommended by glove supplier for protection against materials in Section 2.

EYE PROTECTION

Wear safety spectacles with unperforated sideshields.

SECTION 9 — PHYSICAL AND CHEMICAL PROPERTIES

PRODUCT WEIGHT	10.23 lb/gal	1225 g/l
SPECIFIC GRAVITY	1.23	
BOILING POINT	212 - 449 °F	100 - 231 °C
MELTING POINT	Not Available	
VOLATILE VOLUME	63%	
EVAPORATION RATE	Slower than ether	
VAPOR DENSITY	Heavier than air	
SOLUBILITY IN WATER	Not Available	
pH	> 2.0, < 11.5	
VOLATILE ORGANIC COMPOUNDS (VOC Theoretical - As Packaged)		
0.78 lb/gal	93 g/l	Less Water and Federally Exempt Solvents
0.32 lb/gal	38 g/l	Emitted VOC

SECTION 10 — STABILITY AND REACTIVITY

STABILITY — Stable

CONDITIONS TO AVOID

None known.

INCOMPATIBILITY

None known.

HAZARDOUS DECOMPOSITION PRODUCTS

By fire: Carbon Dioxide, Carbon Monoxide

HAZARDOUS POLYMERIZATION

Will not occur

SECTION 11 — TOXICOLOGICAL INFORMATION

CHRONIC HEALTH HAZARDS

IARC's Monograph No. 93 reports there is sufficient evidence of carcinogenicity in experimental rats exposed to titanium dioxide but inadequate evidence for carcinogenicity in humans and has assigned a Group 2B rating. In addition, the IARC summary concludes, "No significant exposure to titanium dioxide is thought to occur during the use of products in which titanium is bound to other materials, such as paint."

TOXICOLOGY DATA

CAS No.	Ingredient Name			
29911-28-2	1-(2-Butoxymethylethoxy)-propanol	LC50 RAT	4HR	Not Available
		LD50 RAT		Not Available
1317-65-3	Calcium Carbonate	LC50 RAT	4HR	Not Available
		LD50 RAT		Not Available
13463-67-7	Titanium Dioxide	LC50 RAT	4HR	Not Available
		LD50 RAT		Not Available

SECTION 12 — ECOLOGICAL INFORMATION

ECOTOXICOLOGICAL INFORMATION

No data available.

SECTION 13 — DISPOSAL CONSIDERATIONS

WASTE DISPOSAL METHOD

Waste from this product is not hazardous as defined under the Resource Conservation and Recovery Act (RCRA) 40 CFR 261. Incinerate in approved facility. Do not incinerate closed container. Dispose of in accordance with Federal, State/Provincial, and Local regulations regarding pollution.

SECTION 14 — TRANSPORT INFORMATION

Multi-modal shipping descriptions are provided for informational purposes and do not consider container sizes. The presence of a shipping description for a particular mode of transport (ocean, air, etc.), does not indicate that the product is packaged suitably for that mode of transport. All packaging must be reviewed for suitability prior to shipment, and compliance with the applicable regulations is the sole responsibility of the person offering the product for transport.

US Ground (DOT)

Not Regulated for Transportation.

Canada (TDG)

Not Regulated for Transportation.

IMO

Not Regulated for Transportation.

IMO

Not Regulated for Transportation.

IATA/ICAO

Not Regulated for Transportation.

SECTION 15 — REGULATORY INFORMATION**SARA 313 (40 CFR 372.65C) SUPPLIER NOTIFICATION**

CAS No.	CHEMICAL/COMPOUND	% by WT	% Element
7429-90-5	Aluminum		0
	Zinc Compound	1	0.8

CALIFORNIA PROPOSITION 65

WARNING: This product contains chemicals known to the State of California to cause cancer and birth defects or other reproductive harm.

TSCA CERTIFICATION

All chemicals in this product are listed, or are exempt from listing, on the TSCA Inventory.

SECTION 16 — OTHER INFORMATION

This product has been classified in accordance with the hazard criteria of the Canadian Controlled Products Regulations (CPR) and the MSDS contains all of the information required by the CPR.

The above information pertains to this product as currently formulated, and is based on the information available at this time. Addition of reducers or other additives to this product may substantially alter the composition and hazards of the product. Since conditions of use are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information.

SUBMITTAL IDENTIFICATION SHEET

To be completed by Contractor/CM

WEBSTER UNIVERSITY ISB	
PROJECT NAME	
8274 BIG BEND BLVD	
ADDRESS	
NUMBER	
WEBSTER UNIVERSITY	
OWNER	
CANNON DESIGN	
ARCHITECT / ENGINEER	
Joe Voypick	
SUBMITTED BY	
099113-001	
CONTRACTOR / CM SUBMITTAL NO.	CANNON DESIGN SUBMITTAL NO.
	099113
DRAWING / DETAIL REFERENCE	SPECIFICATION SECTION / PARAGRAPH
MANUFACTURER / SUPPLIER	ITEM / PRODUCT ID
REQUIRED DATE	PRIORITY
	☐ CRITICAL

ITEM BEING SUBMITTED (check only one)

- | | | |
|--------------------------------------|---|--|
| ☐ Shop Drawings | ☐ Certification / | ☐ Coordination Drawing |
| ☐ Samples | ☐ Qualifications | ☐ Calculations |
| ☐ (____ copies) | ☐ Record Documents | ☐ Schedules |
| ☐ LEED Submittal | ☒ Product Data | ☐ O&M Manuals |
| ☐ Other _____ | | |

ITEM BEING SUBMITTED FOR (check only one)

- ☒ Action ☐ Information Only ☐ Record

REMARKS OR DEVIATIONS

CONTRACTOR / CM CERTIFICATION (SUBMITTALS NOT CERTIFIED WILL BE RETURNED WITHOUT REVIEW)



PARIC CORPORATION
SUBMITTAL STAMP

THIS SHOP DRAWING HAS BEEN REVIEWED BY PARIC CORPORATION

Subcontractor remains responsible for dimensions, quantities, coordination with other trades and compliance with contract documents.

By:

Devin D. Gates

Joe Voypick	2/8/17
REVIEWED BY	DATE

To be completed by Reviewer

09 9113-001
CANNON DESIGN SUBMITTAL NUMBER
2/9/17
RECEIVED DATE

- ☐ A. No Exceptions Taken
No further review of submittal is required.
- ☐ B. Make Corrections Noted
Incorporate corrections in work; resubmission is not required.
- ☒ C. Revise and Resubmit
Revise as noted, and resubmit for review.
- ☐ D. Rejected
Submittal is not in compliance with Contract Documents; provide new submittal.
- ☐ E. For Record / Information Only
Submittal was reviewed for Record / Information purposes only.
- ☐ F. Not Required for Review
Submittal is not required by Contract Documents and has not been reviewed.

Review is for conformance with the design concept of this project and for general compliance with contract documents. Contractor is responsible for quantities, dimensions and compliance with contract documents and for information that pertains to fabrication processes, construction techniques and coordination of this work with all trades which will be affected thereby. This review is null and void if submittal deviates from contract documents and does not indicate or note deviations.

A/E COMMENTS

☐ See attached sheet(s) for additional comments

See markups.
We need a schedule.
Doors and Frames – east side - match pewter: Web Gray SW 7075
North Door and Frame - tbd.
Door and frame at courtyard - match fiber cement panels. – color tbd.
Railings – powder coating per specification 057300.
Color should match pewter: SW7075 Web Gray

Kelvin Patel	2/23/17
REVIEWED BY	DATE

Digitally signed by Kelvin Patel
DN: C=US, E=kpatel@cannondesign.com, O=Cannon Design,
OU=Architect, CN=Kelvin Patel
Date: 2017.02.23 19:11:05-06'00'



77 Westport Plaza
Suite 250
St. Louis, MO 63146

TRANSMITTAL

No. 15051-0486

Paric Corporation

PROJECT: 15051-Webster University Interdisciplinary Science Building

DATE: 02/08/2017

TO: Cannon Design
1100 Clark Ave
St Louis MO 63102

Fax;
314-241-2203

RE: Exterior painting product data

ATTN: Kelvin Patel

JOB: 15051

WE ARE SENDING:	SUBMITTED FOR:	ACTION TAKEN:
☐ Shop Drawings	☒ Approval	☐ Approved as Submitted
☐ Letter	☐ Your Use	☐ Approved as Noted
☐ Prints	☐ As Requested	☐ Returned After Loan
☐ Change Order	☐ Review and Comment	☐ Resubmit
☐ Plans		☐ Submit
☐ Samples	SENT VIA:	☐ Returned
☐ Specifications	☐ Attached	☐ Returned for Corrections
☒ Other: Product Data	☐ Separate Cover Via:	☒ Due Date: 11/07/2016

<i>Item</i>	<i>Package</i>	<i>Code</i>	<i>Rev.</i>	<i>Copies</i>	<i>Date</i>	<i>Description</i>	<i>Status</i>
Submittal		099113-001	1		02/08/2017	Exterior painting product data	Submitted

NOTES:

CC:

Signed: _____
Devin Gates



Webster University Interdisciplinary Science Building - Exterior

SPECTRA PAINTING COMPANY, LP
13573 SAINT CHARLES ROCK RD
BRIDGETON, MO 630442431

The product data in this submittal for the exterior paints is acceptable. However, please provide plans showing locations of the exterior elements that are to receive these two submitted paint types and the paint color for these exterior elements for Architects review. For example, what gets painted with PT-5 Black magic?

Prepared By:

Mark Cassani
Sales Representative
swrep6270@sherwin.com
(314) 941-0286